



**AMENDMENTS TO THE CLAIMS, COMPLETE LISTING OF CLAIMS**  
**IN ASCENDING ORDER WITH STATUS INDICATOR**

Please amend the following claims as indicated.

1. (Canceled).

2. (Canceled).

3. (Canceled).

4. (Canceled).

5. (Canceled).

6. (Canceled).

7. (Canceled).

8. (Canceled).

9. (Canceled).

10. (Canceled).

11. (Canceled).

12. (Previously Presented) A two-pack type curable resin composition comprising:  
a first liquid containing an epoxy resin and a silyl group-denatured urethane  
prepolymer having an isocyanate group and an alkoxysilyl group in one molecule thereof and a  
weight average molecular weight of 500 or more; and

a second liquid containing a polyamine compound and an alkoxysilyl group-  
condensation catalyst as a curing agent,

wherein the isocyanate compounds from which the silyl group-denatured urethane  
prepolymer is derived contain at least one isocyanate group bonded to an aliphatic secondary or  
tertiary carbon atom.

13. (Previously Presented) A two-pack type curable resin composition comprising:

a first liquid containing an epoxy resin and a silyl group-denatured urethane  
prepolymer having an isocyanate group and an alkoxysilyl group in one molecule thereof and a  
weight average molecular weight of 500 or more; and

a second liquid containing a polyamine compound and an alkoxysilyl group-  
condensation catalyst as a curing agent,

wherein the isocyanate compounds from which the silyl group-denatured urethane  
prepolymer is derived contain at least one isocyanate group bonded to an aliphatic secondary or  
tertiary carbon atom,

wherein the silyl group-denatured urethane prepolymer comprises a reaction product  
obtained by reacting a polyisocyanate compound having two or more isocyanate groups in one  
molecule thereof, and a silane compound having a primary or secondary amino group and an  
alkoxysilyl group in one molecule thereof.

14. (Canceled).

15. (Canceled).

16. (Canceled).

17. (Canceled).